

**RUTOLAN FRANCE**
DEPUIS 1983August 2013
Version :1.1.2**RUTOLAN DOUBLE BOILED LINSEED OIL**

Rutolan DOUBLE BOILED LINSEED OIL is a processed pure raw linseed oil. The oil is slightly oxidised and polymerised during the processing and therefore quick drying.

PROPERTIES: Rutolan DOUBLE BOILED LINSEED OIL is clear and brown/yellow of colour. Rutolan DOUBLE BOILED LINSEED OIL is a very fast drying oil.

APPLICATION : Rutolan DOUBLE BOILED LINSEED OIL is because of the drying characteristics, excellently suitable for manufacturing paint and/or cement or for "greasing" of stain. Rutolan DOUBLE BOILED LINSEED OIL is pre-eminently suitable as a wood preservative and as an agent to protect iron from rust. For the latter mentioned application it is even recommendable to treat metal that is already somewhat rusty.

USE LEVEL: Adding as needed to your extant recipes. If it is used as a wood preservative or antirust-agent to be applied lavishly with a brush.

HANDLING: Rutolan DOUBLE BOILED LINSEED OIL should be handled in accordance with good industrial practice. Consult Material Safety Data Sheet for specific safety and handling information.

STORAGE: Rutolan DOUBLE BOILED LINSEED OIL should be stored between - 10°C and 35°C. Shelf-life if stored in original unopened packaging under the mentioned conditions:
- Rutolan DOUBLE BOILED LINSEED OIL 3 years

WARNING : **Wet fabrics used with water and hang them out or keep them in a closed container after treatment, in order to avoid spontaneous inflammation.**

Technical data	DBLO
Specific gravity, g/cm³, 20°C	0,927 - 0,950
Viscosity, P, 25°C	0,6 - 0,9
Appearance	Liquid
Colour (Gardner), max.	14
Refractive index nD 20°C	1,481 - 1,485
Acid value, mg KOH/g, max	5
Iodine number (Wijs)	170
Saponification number	185 - 215
Insaponifiable, %, max.	1.5
Drying time, 20°C, 65% RH	8 to 15

The technical information and specifications contained in this data sheet are based on careful investigations and given to the best of our knowledge. Nevertheless circumstances under which the product is used in practice are subject to many variations. Rutolan France Sarl cannot be held responsible for possible deviations.

SPECIALISTE DES PRODUITS PROFESSIONNELS DU SECOND-CŒUVRE**Naturellement vert**ADRESSE POSTALE ET BUREAU
RUTOLAN FRANCE SARL
82 RUE DE FENOUILLET
31200 TOULOUSE
TEL. 33 (0)5 61 13 22 22
FAX. 33 (0)5 61 14 31 31SIEGE SOCIAL
RUTOLAN FRANCE SARL
8 BIS, RUE DE LA TRINITE
31000 TOULOUSE
RUTOLAN@RUTOLAN.COM
WWW.RUTOLAN.COMGAMME FLUXAF®
DECAPANTS UNIVERSELS BIODEGRADABLES
PROTECTION ET NETTOYAGE DES SURFACES
ENTRETIEN & PROTECTION DU BOIS
HUILES HOLLANDAISES
MORTIER DE TOITURE FLEXIM®BANQUE POPULAIRE N° 65321701405
BIC CCBPFRPPTLS
IBAN FR76 1780 7008 2165 3217 0140 531
TVA NR. FR 55 329 033 294
RCS TOULOUSE 329 033 294
SIRET 329 033 294 00060